

PASCHIM GUJARAT VIJ COMPANY LTD

SPECIFICATION FOR WOOLEN JERSEY

A. Design Description

Yarn Used : Jersey made of yarn as per below specification

Neck Shape : V-neck

Sleeves : Full Sleeves

Type of Knitting

A. 12 GG, Double bed made

B. Grip at end of sleeves : 2.5 Inch +/- 0.5 Inch of 12 GG

C. Grip at bottom of Body : 2.5 Inch +/- 0.5 Inch of 12 GG

D. Neck Patti of 12 GG, Linking type

E. Thread Used of stitching : Madura Coat or equivalent

F. Shoulder to stitch with DTM cotton type for reinforcement with self dye. All Stitches (shoulder, Armhole & side seams) to be over lock wit machine from inside.

G. Color of woolen jersey : As per PGVCL requirement

H. PGVCL Logo to be printed on Left side chest

I. All jersey to be label with :

- ✓ Brand Name
- ✓ Size
- ✓ Wash care label with composition

J. All jersey to be packed in individual polythene bag with sticker of size on it

B. Size wise Quantity

Size	32"	34"	36"	38"	40"	42"	44"	46"	48"	50"	Total
Total Qty (Nos.)	257	745	1524	1730	1581	1133	526	233	132	102	7963

Width across chest and length of jersey should be as per relevant IS with variation of +/- 5% be allowed.

Signature of Tenderer		Company's Round Seal
Date :	Place :	

PASCHIM GUJARAT VIJ COMPANY LTD

C. Specification for Yarn Used

Sr. No.	Description of test	Requirement
1	Composition	Wool + Acrylic
2	Ratio of Composition	50% Wool (Minimum) + 50% Acrylic
3	Type	Blended
4	Count of Yarn	2/30

Annexure - I

Sr. No.	Description of Test	Requirement as per IS	Test Method as per relevant IS
1.	Composition	Wool & Acrylic	IS:2006 (on dry mass)
2.	Ratio of composition	50% Wool (Min) + 50% Acrylic	IS:744
3.	Dimensional change relaxation shrinkage	5.0% Max	As per clause A-5 of IS:2360
4.	Scouring loss	4.0% Max	As per clause A-6 of IS:2360
5.	Color fastness to		
a)	Light	5 or better	IS : 2454-1967
b)	Washing	4 or better	IS : 3361-1965s

Signature of Tenderer		Company's Round Seal
Date :	Place :	